



WINTRADE S.r.l.
CHROME PLATED BARS • STEEL TUBES • SPECIAL STEELS

ACCIAI FERRITICI

DESIGNAZIONE E NORME DI RIFERIMENTO				COMPOSIZIONE CHIMICA SECONDO EN 10083-3										
EN 10083-3	UNI	DIN	AFNOR	BS 970	AISI	C	Si	Mn	P	S	Cr	Ni	Mo	Others
max		17440 SEW 400	35-574 35-578			max	max	max	max					
1.4016X6Cr17	X8Cr17	1.4016	Z8C17	430S17	430	< 0.08	01.00	01.00	0.040	0.030	16/18	-	-	-
1.4104X14CrMoS17	X10CrMoS17	1.4104	Z13CF17	-	(430F)	0.10/0.17	01.00	01.50	0.040	0.15/0.35	15.5/17.5	-	0.20/0.60	-